

Amendments to the Claims

1. Cancelled

2. (Amended) A carbinol-functional silicone resin of claim 20+ wherein
the alkyl group is methyl;
the aryl group is phenyl;
the carbinol group free of aryl groups having at least 3 carbon atoms is selected from a group
having the formula R^4OH wherein R^4 is selected from

- (1) a group having the formula $-(CH_2)_x-$ where x has a value of 3 to 10,
- (2) $-CH_2CH(CH_3)-$,
- (3) $-CH_2CH(CH_3)CH_2-$,
- (4) $-CH_2CH_2CH(CH_2CH_3)CH_2CH_2CH_2-$, and
- (5) a group having the formula $-OCH(CH_3)(CH_2)_x-$ wherein x has a value of 1 to 10

and a group having the formula $R^6(OH)$ wherein R^6 is a group having the formula -
 $CH_2CH_2(CH_2)_xOCH_2CH-$ wherein x in each case has a value of 1 to 10;
the aryl-containing carbinol group having at least 6 carbon atoms is a group having the
formula R^5OH wherein R^5 is selected from

- (1) a group having the formula $-(CH_2)_xC_6H_4-$ wherein x has a value of 0 to 10,
- (2) a group having the formula $-CH_2CH(CH_3)(CH_2)_xC_6H_4-$ wherein x has a value of
0 to 10, and
- (3) a group having the formula $-(CH_2)_xC_6H_4(CH_2)_x-$ wherein x has a value of 1 to
10.

3. (Original) A carbinol-functional silicone resin comprising the units:

$(R^1_3SiO_{1/2})_a$ (i)

$(R^2_2SiO_{2/2})_b$ (ii)

$(R^3SiO_{3/2})_c$ (iii) and




$(SiO_{4/2})_d$ (iv)

wherein R^1 is independently a hydrogen atom, an alkyl group having from 1 to 8 carbon atoms, an aryl group, a carbinol group free of aryl groups having at least 6 carbon atoms, or an aryl-containing carbinol group having at least 6 carbon atoms, R^2 is a hydrogen atom, an alkyl group having from 1 to 8 carbon atoms, an aryl group, a carbinol group free of aryl groups having at least 3 carbon atoms, or an aryl-containing carbinol group having at least 6 carbon atoms, R^3 is an alkyl group having from 1 to 8 carbon atoms or an aryl group, a has a value of less than or equal to 0.6, b has a value of zero or greater than zero, c has a value of greater than zero, d has a value of less than 0.5, and the value of $a + b + c + d = 1$, and with the proviso that when each R^2 is methyl the value of b is less than 0.3 and with the proviso that greater than 25 wt% of the $R^1 + R^2 + R^3$ groups in the carbinol-functional silicone resin are phenyl.

4. (Amended) The carbinol-functional silicone resin of ~~any of Claims 201 to 3~~ where a has a typical value of 0.1 to 0.6, b has a typical value of 0 to 0.4, c has a typical value of 0.3 to 0.8, and d has a typical value of 0 to 0.3.

5. (Amended) The carbinol-functional silicone resin according to Claim ~~201 or 2~~ wherein the carbinol-functional silicone resin is selected from

carbinol-functional silicone resins comprising the units:




carbinol-functional silicone resins comprising the units:




carbinol-functional silicone resins comprising the units:




carbinol-functional silicone resins comprising the units:




carbinol-functional silicone resins comprising the units:




carbinol-functional silicone resins comprising the units:




carbinol-functional silicone resins comprising the units:



carbinol-functional silicone resins comprising the units:



~~carbinol-functional silicone resins comprising the units:~~







wherein a has a typical value of 0.1 to 0.6, b has a typical value of zero to 0.4, and c has a typical value of 0.3 to 0.8.

5. (Cancelled)

6. (Amended) A method of preparing carbinol-functional silicone resins comprising reacting:





(A') at least one hydrogen-functional silicone resin comprising the units:



wherein R^7 and R^8 are each independently an alkyl group having from 1 to 8 carbon atoms, an aryl group, or a hydrogen atom, R^3 is an alkyl group having from 1 to 8 carbon atoms or an aryl group, a has a value of less than or equal to 0.6, b has a value of zero or greater than zero, c has a value of greater than zero, d has a value of less than 0.5, the value of $a + b + c + d = 1$, with the proviso that when each R^8 is methyl the value of b is less than 0.3, with the proviso that there are at least two silicon-bonded hydrogen atoms present in the silicone resin, and with the proviso that greater than 10 wt% of the $R^7+R^8+R^3$ groups are phenyl; and (B') at least one vinyl-terminated alcohol; in the presence of (C') a hydrosilylation catalyst; and optionally (D') at least one solvent.

7. (Original) A method of preparing carbinol-functional silicone resins comprising reacting:

(A') at least one hydrogen-functional silicone resin comprising the units:






wherein R^7 and R^8 are each independently an alkyl group having from 1 to 8 carbon atoms, an aryl group, or a hydrogen atom, R^3 is an alkyl group having from 1 to 8 carbon atoms or an aryl group, a has a value of less than or equal to 0.6, b has a value of zero or greater than zero, c has a value of greater than zero, d has a value of less than 0.5, the value of $a + b + c + d = 1$, with the proviso that when each R^8 is methyl the value of b is less than 0.3, with the

Page 6 of 14


proviso that there are at least two silicon-bonded hydrogen atoms present in the silicone resin and with the proviso that greater than 30 wt% of the $R^1 + R^2 + R^3$ groups are phenyl; and (B') at least one vinyl-terminated alcohol; in the presence of (C') a hydrosilylation catalyst; and optionally (D') at least one solvent.

8. (Amended) The method of preparing carbinol-functional silicone resins according to Claim 6 or 7 where a has a typical value of 0.1 to 0.6, b has a typical value of 0 to 0.4, c has a typical value of 0.3 to 0.8, and d has a typical value of 0 to 0.3.


9. (Original) The method of preparing carbinol-functional silicone resins according to Claim 6 where the hydrogen-functional silicone resins of (A) are selected from hydrogen-functional silicone resins comprising the units:





hydrogen-functional silicone resins comprising the units:



hydrogen-functional silicone resins comprising the units:






hydrogen-functional silicone resins comprising the units:



and





hydrogen-functional silicone resins comprising the units:





wherein a has a typical value of 0.1 to 0.6, b has a typical value of 0 to 0.4, and c has a typical value of 0.3 to 0.8.

10. (Original) An emulsion composition comprising: (A) a carbinol-functional silicone resin comprising the units:



wherein R^1 and R^2 are each independently a hydrogen atom, an alkyl group having from 1 to 8 carbon atoms, an aryl group, a carbinol group free of aryl groups having at least 3 carbon atoms, or an aryl-containing carbinol group having at least 6 carbon atoms, R^3 is an alkyl group having from 1 to 8 carbon atoms or an aryl group, a has a value of less than or equal to 0.6, b has a value of zero or greater than zero, c has a value of greater than zero, d has a value of less than 0.5, and the value of $a + b + c + d = 1$, and with the proviso that when each R^2 is methyl the value of b is less than 0.3, and with the proviso there is on average at least one carbinol group per resin molecule; (B) at least one surfactant; and (C) water.

11. (Amended) The emulsion composition according to claim 10 wherein the alkyl group is methyl;
the aryl group is phenyl;
the carbinol group free of aryl groups having at least 3 carbon atoms is selected from a group having the formula R^4OH wherein R^4 is selected from

(1) a group having the formula $-(\text{CH}_2)_x-$ where x has a value of 3 to 10,

(2) $-\text{CH}_2\text{CH}(\text{CH}_3)-$,

(3) $-\text{CH}_2\text{CH}(\text{CH}_3)\text{CH}_2-$,

(4) $-\text{CH}_2\text{CH}_2\text{CH}(\text{CH}_2\text{CH}_3)\text{CH}_2\text{CH}_2\text{CH}_2-$, and

(5) a group having the formula $-\text{OCH}(\text{CH}_3)(\text{CH}_2)_x-$ wherein x has a value of 1 to 10

and a group having the formula $R^6(OH)$ wherein R^6 is a group having the formula - $CH_2CH_2(CH_2)_xOCH_2CH_2-$ wherein x in each case has a value of 1 to 10;

the aryl-containing carbinol group having at least 6 carbon atoms is a group having the formula R^5OH wherein R^5 is selected from

~~(4)-(1)~~ a group having the formula $-(CH_2)_xC_6H_4-$ wherein x has a value of 0 to 10,




~~(5)-(2)~~ a group having the formula $-CH_2CH(CH_3)(CH_2)_xC_6H_4-$ wherein x has a value of 0 to 10, and

~~(3)~~ a group having the formula $-(CH_2)_xC_6H_4(CH_2)_x-$ wherein x has a value of 1 to

10.

12. (Amended) The emulsion composition according to Claim 10 ~~or 11~~ wherein where a has a typical value of 0.1 to 0.6, b has a typical value of 0 to 0.4, c has a typical value of 0.3 to 0.8, and d has a typical value of 0 to 0.3.

13. (Amended) The emulsion composition according to Claim 10 ~~or 11~~ wherein the carbinol-functional silicone resin is selected from carbinol-functional silicone resins comprising the units:




carbinol-functional silicone resins comprising the units:



carbinol-functional silicone resins comprising the units:





carbinol-functional silicone resins comprising the units:










carbinol-functional silicone resins comprising the units:



carbinol-functional silicone resins comprising the units:




carbinol-functional silicone resins comprising the units:



carbinol-functional silicone resins comprising the units:



carbinol-functional silicone resins comprising the units:



wherein a has a typical value of 0.1 to 0.6, b has a typical value of zero to 0.4, and c has a typical value of 0.3 to 0.8.




14. (Amended) The emulsion composition according to ~~any of Claims 10 to 13~~, wherein greater than 10 weight percent of the $\text{R}^1 + \text{R}^2 + \text{R}^3$ groups are phenyl.

15. (Amended) The emulsion composition according to ~~any of Claims 10 to 14~~ wherein the emulsion composition further comprises at least one ingredient selected from

fragrances, preservatives, vitamins, ceramides, amino-acid derivatives, liposomes, polyols, botanicals, conditioning agents, glycols, vitamin A, vitamin C, vitamin E, Pro-Vitamin B5, sunscreen agents, humectants, preservatives, emollients, occlusive agents, esters, pigments, and self-tanning agents.

16. (New) The carbinol-functional silicone resin according to Claim 20, wherein greater than 25 weight percent of the $R^1+R^2+R^3$ groups are phenyl.

17. (New) The carbinol-functional silicone resin according to Claim 3 wherein the carbinol-functional silicone resin is selected from carbinol-functional silicone resins comprising the units:




carbinol-functional silicone resins comprising the units:





carbinol-functional silicone resins comprising the units:






carbinol-functional silicone resins comprising the units:





carbinol-functional silicone resins comprising the units:




carbinol-functional silicone resins comprising the units:




carbinol-functional silicone resins comprising the units:



carbinol-functional silicone resins comprising the units:



~~carbinol-functional silicone resins comprising the units:~~






wherein a has a typical value of 0.1 to 0.6, b has a typical value of zero to 0.4, and c has a typical value of 0.3 to 0.8.

18. (New) The method of preparing carbinol-functional silicone resins according to Claim 6 where a has a typical value of 0.1 to 0.6, b has a typical value of 0 to 0.4, c has a typical value of 0.3 to 0.8, and d has a typical value of 0 to 0.3.

19. (New) The emulsion composition according to Claim 14 wherein the emulsion composition further comprises at least one ingredient selected from fragrances, preservatives, vitamins, ceramides, amino-acid derivatives, liposomes, polyols, botanicals, conditioning agents, glycols, vitamin A, vitamin C, vitamin E, Pro-Vitamin B5, sunscreen agents, humectants, preservatives, emollients, occlusive agents, esters, pigments, and self-tanning agents.

20. (New) A carbinol-functional silicone resin comprising the units:



wherein R^1 and R^2 are each independently a hydrogen atom, an alkyl group having from 1 to 8 carbon atoms, an aryl group, a carbinol group free of aryl groups having at least 3 carbon atoms, or an aryl-containing carbinol group having at least 6 carbon atoms, R^3 is an alkyl group having from 1 to 8 carbon atoms or an aryl group, a has a value of less than or equal to 0.6, b has a value of zero or greater than zero, c has a value of greater than zero, d has a value of less than 0.5, and the value of $a + b + c + d = 1$, with the proviso that when each R^2 is methyl the value of b is less than 0.3 and with the proviso there is on average at least one carbinol group per resin molecule and greater than 10 wt% of the $R^1+R^2+R^3$ groups in the carbinol-functional silicone resin are phenyl.